

H13

TOOL STEEL

H13 is a high-performance hot work tool steel with excellent thermal fatigue resistance, hardenability, wear resistance, and toughness. It is commonly used in hot and cold work tooling, but is particularly well-suited for hot work applications due to its exceptional properties.


H13 is harder and more abrasion-resistant than most mild and stainless steels, but less hard than other tool steels like D2. Its combination of properties makes it a versatile and reliable choice for a range of applications.

Composition	Weight%	Features & Benefits
Iron	Balance	Resistant to thermal fatigue
Carbon	0.4	Hardenable
Chromium	5.0	Great wear resistance and toughness
Manganese	0.4	Variable properties through heat treatments
Molybdenum	1.2	
Silicon	1.0	
Vanadium	1.0	


*Related standards and denominations: AISI H13, ASTM A681, 1.2344 / X40CrMoV5-1, UNS T20813, JIS G4404 SKD61

Physical Properties	As Sintered	As Annealed	H+T*
Ultimate tensile strength [MPa]	1350	625	1200-1450
Yield strength [MPa]	800	285	1000-1300
Elongation [%]	3	>15	4-10
Hardness [HRC]	40	<20	44-52
Relative density [%]	97	97	97

* H=Hardened, T=Tempered. Final properties vary depending on heat treatment conditions.



As sintered and annealed



H+T

These representative data were tested, measured, or calculated using standard methods and are subject to change without notice. Markforged makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement; and assumes no liability in connection with the use of this information. The data listed here should not be used to establish design, quality control, or specification limits, and are not intended to substitute for your own testing to determine suitability for your particular application. Nothing in this sheet is to be construed as a license to operate under or a recommendation to infringe upon any intellectual property right.